Safety data sheet according to Regulation (EC) No 1907/2006, Article 31

	accora	ling to Regulation (EC) No 1907/2006, Article 3	31
Printing date 27.03.	2024	Version number 4 (replaces version 3)	Revision: 27.03.2024
SECTION 1.	Identifica	tion of the substance/mixture and of the co	mpany/undertaking
· 1.1 Product ide Trade name: <u>H</u> Article number	ARDINOX -	<u>Stainless steel paint</u> /12444 UFI : FCXA-M5WU-J300-KAP3	
No further relev Sector of Use SU21 Consum SU22 Professi Product categor Process categor PROC7 Indust PROC11 Non	ant informati er uses: Priva onal uses: Pu y PC9a Coa y rial spraying industrial spr	ate households / general public / consumers blic domain (administration, education, entertainmen atings and paints, thinners, paint removers	
Manufacturer/S A.M.P.E.R.E. S 3 rue Antoine B Z.I. du Vert Gal 95310 Saint-Ou FRANCE Têlêphone: + 3. fds@amperesys	S upplier: YSTEM alard ant en-I'Aumône 3 1 34 64 72 7 tem.com		
· Ireland : Nation	al Poisons In	a mber: UK : National Poisons Information Service - 0 Iformation Centre - Beaumont Hospital - PO Box 129 Iealthcare professionals-24/7) - +353 1 809 2166 (pu	7 Beaumont Road 9
SECTION 2.	Hazards i	dentification	
	ccording to I	stance or mixture Regulation (EC) No 1272/2008	
Aerosol 1	H222-H2	29 Extremely flammable aerosol. Pressurised contain	her: May burst if heatea.
Eye Irrit. 2	H319	Causes serious eye irritation.	
STOT SE 3	H336	May cause drowsiness or dizziness.	
Aquatic Chroni	c 3 H412	Harmful to aquatic life with long lasting effects.	
	ding to Regue classified and	elation (EC) No 1272/2008 labelled according to the GB CLP regulation.	
	>		
GHS02 GHS	507		
			(Contd. on page 2)

(Contd. on page 2) GB Page 2/12

Safety data sheet according to Regulation (EC) No 1907/2006, Article 31

Printing date 27.03.2024

Version number 4 (replaces version 3)

Revision: 27.03.2024

Trade name: HARDINOX - Stainless steel paint

Signal	(Contd. of page 1)
0	ord Danger
	determining components of labelling:
acetone	
ethyl ace	
•	rbons, C9, aromatics
	tatements
H222-H2	229 Extremely flammable aerosol. Pressurised container: May burst if heated.
H319	Causes serious eye irritation.
H336	May cause drowsiness or dizziness.
H412	Harmful to aquatic life with long lasting effects.
Precauti	onary statements
P101	If medical advice is needed, have product container or label at hand.
P102	Keep out of reach of children.
P210	Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.
P211	Do not spray on an open flame or other ignition source.
P251	Do not pierce or burn, even after use.
P260	Do not breathe spray.
P410+P4	412 Protect from sunlight. Do not expose to temperatures exceeding 50 °C/122 °F.
P501	Dispose of contents / container in accordance with regional regulations.
Addition	al information:
	Repeated exposure may cause skin dryness or cracking.
	Contains nickel powder, methyl methacrylate, n-butyl methacrylate. May produce an allergic
	reaction.
Buildup	of explosive mixtures possible without sufficient ventilation.
-	r hazards
	f PBT and vPvB assessment
	t applicable.

· vPvB: Not applicable.

SECTION 3: Composition/information on ingredients

· 3.2 Mixtures

 $\cdot \textit{Description: Mixture of substances listed below with nonhazardous additions.}$

Dangerous components:		
CAS: 67-64-1 EINECS: 200-662-2 Index number: 606-001-00-8 Reg.nr.: 01-2119471330-49	acetone Flam. Liq. 2, H225 Eye Irrit. 2, H319; STOT SE 3, H336 EUH066	12.5-<20%
CAS: 74-98-6 EINECS: 200-827-9 Index number: 601-003-00-5 Reg.nr.: 01-2119486944-21	propane Flam. Gas 1A, H220 Press. Gas (Comp.), H280	12.5-<20%
CAS: 106-97-8 EINECS: 203-448-7 Index number: 601-004-00-0 Reg.nr.: 01-2119474691-32	butane (containing < 0,1 % butadiene (203-450-8)) Flam. Gas IA, H220 Press. Gas (Comp.), H280	12.5-<20%
CAS: 141-78-6 EINECS: 205-500-4 Index number: 607-022-00-5 Reg.nr.: 01-2119475103-46	ethyl acetate Flam. Liq. 2, H225 Eye Irrit. 2, H319; STOT SE 3, H336 EUH066	12.5-<20%
EC number: 905-588-0 Index number: 601-022-00-9 Reg.nr.: 01-2119488216-32	xylene Flam. Liq. 3, H226 STOT RE 2, H373; Asp. Tox. 1, H304 Acute Tox. 4, H312; Acute Tox. 4, H332; Skin Irrit. 2, H315; Eye Irrit. 2, H319; STOT SE 3, H335	5-<10%
		(Contd. on page

according to Regulation (EC) No 1907/2006, Article 31

Printing date 27.03.2024

Version number 4 (replaces version 3)

Revision: 27.03.2024

Trade name: HARDINOX - Stainless steel paint

		(Contd. of page 2)
EC number: 918-668-5	Hydrocarbons, C9, aromatics	5-<10%
Reg.nr.: 01-2119455851-35	 Flam. Liq. 3, H226 Asp. Tox. 1, H304 	
	Aquatic Chronic 2, H411	
	♦ STOT SE 3, H335-H336 EUH066	
CAS: 75-28-5	isobutane (containing $< 0,1$ % butadiene (203-450-8))	5-<10%
EINECS: 200-857-2	🚸 Flam. Gas 1A, H220	
Index number: 601-004-00-0 Reg.nr.: 01-2119485395-27	Press. Gas (Comp.), H280	
EC number: 918-481-9 Reg.nr.: 01-2119457273-39	<i>Hydrocarbons, C10-C13, n-alkanes, isoalkanes, cyclics, < 2% aromatics</i>	2.5-<5%
Keg.m. 01-2119457275-59	(3) Asp. Tox. 1, H304 EUH066	-
CAS: 1314-13-2	zinc oxide	≥0.25-≤0.5%
EINECS: 215-222-5 Index number: 030-013-00-7 Reg.nr.: 01-2119463881-32	Sequatic Acute 1, H400; Aquatic Chronic 1, H410	
CAS: 7440-02-0	nickel powder	≥0.1-≤0.5%
EINECS: 231-111-4 Index number: 028-002-01-4	Carc. 2, H351; STOT RE 1, H372 Skin Sens. 1, H317	
Reg.nr.: 01-2119438727-29	Aquatic Chronic 3, H412	
CAS: 80-62-6	methyl methacrylate	≥0.1-≤0.5%
EINECS: 201-297-1 Index number: 607-035-00-6	Flam. Liq. 2, H225	
CAS: 97-88-1	Skin Irrif. 2, H315; Skin Sens. 1, H317; STOT SE 3, H335	≥0.1-≤0.5%
EINECS: 202-615-1	<i>n-butyl methacrylate</i>	20.1-20.3%
Index number: 607-033-00-5	 Flam. Liq. 3, H226 Skin Irrit. 2, H315; Eye Irrit. 2, H319; Skin Sens. 1, H317; 	
Reg.nr.: 01-2119486394-28	STOT SE 3, H335	

· Additional information:

The content of Benzene (EINECS-Nr. 200-753-7) in the ingredients is less than 0,1% (Note P Annex 1A 1272/2008 EU), so the classification as carcinogen need not to apply. xylene: Contains ethylbenzene CAS 100-41-4

For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

· 4.1 Description of first aid measures

· After inhalation: Supply fresh air; consult doctor in case of complaints.

· After skin contact: Generally the product does not irritate the skin.

· After eye contact:

Rinse opened eye for several minutes under running water. If symptoms persist, consult a doctor.

- After swallowing: Drink plenty of water and provide fresh air. Call for a doctor immediately.
- 4.2 Most important symptoms and effects, both acute and delayed No further relevant information available.

• **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

SECTION 5: Firefighting measures

· 5.1 Extinguishing media

· Suitable extinguishing agents:

CO2, powder or water spray. Fight larger fires with water spray or alcohol resistant foam. Use fire extinguishing methods suitable to surrounding conditions.

· 5.2 Special hazards arising from the substance or mixture

During heating or in case of fire poisonous gases are produced.

(Contd. on page 4)

GB

according to Regulation (EC) No 1907/2006, Article 31

Printing date 27.03.2024

Version number 4 (replaces version 3)

Revision: 27.03.2024

(Contd. of page 3)

Trade name: HARDINOX - Stainless steel paint

- · 5.3 Advice for firefighters -
- · Protective equipment: Mouth respiratory protective device.

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Mount respiratory protective device.
 Wear protective equipment. Keep unprotected persons away.
 Keep away from ignition sources.
 6.2 Environmental precautions: Inform respective authorities in case of seepage into water course or sewage system. Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up: Dispose contaminated material as waste according to section 13. Ensure adequate ventilation.
- 6.4 Reference to other sections
 See Section 7 for information on safe handling.
 See Section 8 for information on personal protection equipment.
 See Section 13 for disposal information.

SECTION 7: Handling and storage

- · 7.1 Precautions for safe handling Ensure good ventilation/exhaustion at the workplace.
- *Information about fire and explosion protection: Keep ignition sources away - Do not smoke. Keep respiratory protective device available.*
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage:
- Requirements to be met by storerooms and receptacles:

Observe official regulations on storing packagings with pressurised containers.

- · Information about storage in one common storage facility: Not required.
- Further information about storage conditions: Keep container tightly sealed.
- · Storage class: 2 B
- · 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

Ingredients with limit values that require monitoring at the workplace	e:
67-64-1 acetone	
WEL Short-term value: 3620 mg/m³, 1500 ppm	
Long-term value: 1210 mg/m³, 500 ppm	
106-97-8 butane (containing < 0,1 % butadiene (203-450-8))	
WEL Short-term value: 1810 mg/m ³ , 750 ppm	
Long-term value: 1450 mg/m ³ , 600 ppm	
<i>Carc</i> (<i>if more than</i> 0.1% <i>of buta-1.3-diene</i>)	
141-78-6 ethyl acetate	
WEL Short-term value: 1468 mg/m³, 400 ppm	
Long-term value: 734 mg/m ³ , 200 ppm	
xylene	
WEL Short-term value: 441 mg/m ³ , 100 ppm	
Long-term value: 220 mg/m ³ , 50 ppm	
Sk; BMGV	
	(Contd. on pag

Safety data sheet according to Regulation (EC) No 1907/2006, Article 31

Printing date 27.03.2024

Version number 4 (replaces version 3)

Revision: 27.03.2024

Trade name: HARDINOX - Stainless steel paint

7440-02-0	nickel 1	nowder	(Contd. of pag		
	ig-term value: 0.5 mg/m ³				
	Ni; Sk; Carc				
80-62-6 m	ethyl me	ethacrylate			
		alue: 416 mg/m³, 100 ppm			
Long	g-term v	alue: 208 mg/m³, 50 ppm			
DNELs					
67-64-1 ac					
Oral		62 mg/kg /per day (Consumer, longterm systemic)			
Dermal		62 mg/kg /per day (Consumer, longterm systemic)			
		186 mg/kg /per day (Worker, longterm systemic)			
Inhalative		2420 mg/m3 (Worker, acute local)			
		1210 mg/m3 (Worker, longterm systemic)			
		200 mg/m3 (Consumer, longterm systemic)			
		60 mg/m3			
141-78-6 e	-				
Oral		4.5 mg/kg /per day (Consumer, longterm systemic)			
Dermal		63 mg/kg /per day (Worker, longterm systemic)			
		37 mg/kg /per day (Consumer, longterm systemic)			
Inhalative		734 mg/m3 /200 ppm (Worker, longterm systemic)			
		1468 mg/m3 /400 ppm (Worker, acute systemic)			
		734 mg/m3 /200 ppm (Worker, longterm local)			
		1468 mg/m3 /400 ppm (Worker, acute local)			
		367 mg/m3 /100 ppm (Consumer, longterm systemic)			
		734 mg/m3 /200 ppm (Consumer; acute systemic)			
		367 mg/m3 /100 ppm (Consumer, longterm local)			
	DNEL	734 mg/m3 /200 ppm (Consumer, acute local)			
xylene	DUEL				
Oral		1.6 mg/kg /per day (Consumer, longterm systemic)			
Dermal		180 mg/kg /per day (Worker, longterm systemic)			
Inhalative		211 mg/m3 (Worker, longterm systemic)			
		221 mg/m3 (Worker, longterm local)			
		442 mg/m3 (Worker, acute systemic)			
		289 mg/m3 (Worker, acute local)			
		14.8 mg/m3 (Consumer, longterm systemic)			
		260 mg/m3 (Consumer; acute systemic)			
		65.3 mg/m3 (Consumer, longterm local)			
Hudmonart		260 mg/m3 (Consumer, acute local) , aromatics			
÷		, aromancs 11 mg/kg /per day (Consumer, longterm systemic)			
Orai Dermal		25 mg/kg /per day (Consumer, longterm systemic)			
Dermal		11 mg/kg /per day (Worker, longterm systemic) 11 mg/kg /per day (Consumer, longterm systemic)			
Inhalative		11 mg/kg /per day (Consumer, longterm systemic) 150 mg/m3 (Worker, longterm systemic)			
maaanve		32 mg/m3 (Worker, longterm systemic)			
DVEC	DNEL	52 mg/m5 (Consumer, congretin systemic)			
PNECs	- 1 -				
67-64-1 ac		Freshwater)			

GB

Safety data sheet according to Regulation (EC) No 1907/2006, Article 31

Printing date 27.03.2024

Version number 4 (replaces version 3)

Revision: 27.03.2024

Trade name: HARDINOX - Stainless steel paint

IContd. of page PNEC 1.06 mg/l (Seawater) PNEC 21 mg/l (Sporadic release) PNEC 100 mg/l (Sewage treatment plant) PNEC 3.04 mg/g (Seawater sediment) PNEC 29.5 mg/g (Soil) Ingredients with biological limit values: system BMCV 650 mmol/mol creatinine Medium: urine Sampling time: post shift Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / jumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes		
PNEC 21 mg/l (Sporadic release) PNEC 100 mg/l (Sewage treatment plant) PNEC 100 mg/l (Sewage treatment plant) PNEC 100 mg/l (Sewage treatment plant) PNEC 20.4 mg/kg (Fershwater sediment) PNEC 29.5 mg/kg (Soil) Impredients with biological limit values: xyteme Symple BMGV BMGV 50 mmol/mol creatinine Medium: urine Sampling time: post shift Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs. beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / finnes / aerosols. Avoid contact with the eyes. Respiratory protection: Void Inoger exposure use self-contained respiratory protective device. Inger exposure use self-contained respiratory protective device. In case of intensive or longer exposure or low pollution use respiratory filter device. Inger exposure	DNEC	
PNEC 100 mg/t (Sewage treatment plant) PNEC 30.4 mg/kg (Freshwater sediment) PNEC 2.5 mg/kg (Sawater sediment) Promediaters with biological limit values: xyten		
PNEC 3.04 mg/kg (Freshwater sediment) PNEC 29.5 mg/kg (Seavater sediment) PNEC 29.5 mg/kg (Seavater sediment) PNEC 29.5 mg/kg (Soil) Ingreations with biological limit values:		
PNEC 3.04 mg/kg (Seawater sediment) PNEC 29.5 mg/kg (Soil) Ingredients with biological limit values:		
PNEC 29.5 mg/kg (Soil) Ingredients with biological limit values: cylene BMGV 650 mmol/mol creatinine Medium: urine Sampling time: post shift Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Respiratory protection: Void contact with the eyes. Respiratory protection: Filter A2/P3 In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 In protection Material of gloves In case of low enderial Busy rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Busy labele gloves with a thickness of 0.4 mm	PNEC	30.4 mg/kg (Freshwater sediment)
Ingredients with biological limit values: sylene BMGV 650 mmol/mol creatinine Medium: urine Sampling time: post shift Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Respiratory protection: Void contact with the eyes. Respiratory protection: Filter A2/P3 Hand protection Protective gloves Busyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualit and varies from manufacturer to manufacturer. Penetration time of glove material Busyl nubber, BR Busyl rubber, BR Busyl rubber, BR Busyl rubber, gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Busyl acetate: 170 min Xylene: 42 min Busyl nubber gloves and a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length in particular cases.	PNEC	3.04 mg/kg (Seawater sediment)
xylene BMGV 650 mmol/mol creatinine Medium: urine Sampling time: post shift Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / funes / aerosols. Avoid contact with the eyes. Respiratory protection: Vooid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Ethyl acetate: 170 min Xylen: 42 min Butyl cubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length in particular cases.	PNEC	29.5 mg/kg (Soil)
BMGV 650 mmol/mol creatinine Medium: wrine Sampling time: post shift Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / funes / aerosols. Avoid contact with the eyes. Respiratory protection: World Ontact with the eyes. Respiratory protection: Noid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Washyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber, gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl cubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length in particular cases.	Ingred	lients with biological limit values:
Medium: urine Sampling time: post shift Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / finnes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: Image: approximation of the second skin. Avoid contact with the eyes. Respiratory protection: Image: approximation of the second skin. Avoid contact with the eyes. Respiratory protection: Image: approximation of the second skin. Avoid contact with the eyes. Filter A2/P3 Hand protection Image: approximation of the second skin. Avoid contact with the eyes. Filter A2/P3 Hand protection Protective gloves Batyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualit and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Ethyl acetate: 00 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length in particular cases.	•	
Sampling time: post shift Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: Image: A consols. In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Matrial of gloves Buryl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualit and varies from manufacturer to manufacturer. Parteriation time of glove material Buryl rubber, gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Buryl acetate: 170 min Xylene: 42 min Buryl acetate: 170 min Xylene: 42 min Buryl nubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance lengt in particular cases. <td>BMGV</td> <td></td>	BMGV	
Parameter: methyl hippuric acid Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all solled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: Image: Control of the system or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Image: Structure gloves Parterial of gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber, gloves with a thickness of 0.4 mm are resistant to: Accence: 480 min Etyl accetae: 170 min Sylene: 42 min Butyl		
Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Respiratory protection: Novid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Protective gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Accetore: #30 min Butyl acetate: 100 min Ethyl acetate: 170 min Xylene: 42 min Butyl acetate: 170 min Xylene: 42 min Butyl Buty River Sum and the users and responsible persons for work safety assume solvent resistance length in particular cases.		
 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Work Protective gloves Material of gloves Buyl nubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualit and varies from manufacturer to manufacturer. Pentration time of glove material Butyl rubber, gloves with a thickness of 0.4 mm are resistant to: Accetone: 480 min Butyl acetate: 60 min Etyl acetate: 70 min Sylene: 42 min Butyl acetate: 70 min Sylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure: we recommend that users and responsible persons for work safety assume solvent resistance length in particular cases.	A T T	
Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: Image: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Image: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Image: In the selection of the suitable gloves does not only depend on the material, but also on further marks of qualitient varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber, BR The selection of the suitable gloves of 0.4 mm are resistant to: Accetone: 480 min Butyl acetate: 170 min Sylene: 42 min Butyl acetate: 170 min <	Additio	onal information: The lists valid during the making were used as basis.
Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: Image: Image		
General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Work Protective gloves Material of gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualit and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acctone: 480 min Butyl acctate: 60 min Ethyl acctate: 60 min Ethyl acctate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length in particular cases.		
Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / funes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection:		
Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection:		
 Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Protective gloves Material of gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualitand varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Accetone: 480 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42-480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases. 		
Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection:		
 Avoid contact with the eyes and skin. Avoid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection With the eyes Protective gloves Material of gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Pertention time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Accetone: 480 min Euryl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 12 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance lengt in particular cases.		
Avoid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Filter A2/P3 Hand protection Protective gloves Material of gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualit and varies from manufacturer to manufacturer. Pretration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Eutyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		0
In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Material of gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualit and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.	Avoid a	contact with the eyes.
 Ionger exposure use self-contained respiratory protective device. Filter A2/P3 Hand protection Protective gloves Material of gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of qualitand varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length in particular cases. 	Respire	atory protection:
 Hand protection Protective gloves Material of gloves Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length in particular cases. 		
Protective glovesMaterial of glovesButyl rubber, BRThe selection of the suitable gloves does not only depend on the material, but also on further marks of qualiand varies from manufacturer to manufacturer.Penetration time of glove materialButyl rubber gloves with a thickness of 0.4 mm are resistant to:Acetone: 480 minButyl acetate: 60 minEthyl acetate: 170 minXylene: 42 minButyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protectivemeasure, we recommend that users and responsible persons for work safety assume solvent resistance length inparticular cases.		
Material of glovesButyl rubber, BRThe selection of the suitable gloves does not only depend on the material, but also on further marks of qualitand varies from manufacturer to manufacturer.Penetration time of glove materialButyl rubber gloves with a thickness of 0.4 mm are resistant to:Acetone: 480 minButyl acetate: 60 minEthyl acetate: 170 minXylene: 42 minButyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protectivemeasure, we recommend that users and responsible persons for work safety assume solvent resistance length inof 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in	Hand J	protection
Material of glovesButyl rubber, BRThe selection of the suitable gloves does not only depend on the material, but also on further marks of qualiand varies from manufacturer to manufacturer.Penetration time of glove materialButyl rubber gloves with a thickness of 0.4 mm are resistant to:Acetone: 480 minButyl acetate: 60 minEthyl acetate: 170 minXylene: 42 minButyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protectivemeasure, we recommend that users and responsible persons for work safety assume solvent resistance length inof 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in	ſM	
Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		Protective gloves
Butyl rubber, BR The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.	V	
The selection of the suitable gloves does not only depend on the material, but also on further marks of quali and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		
and varies from manufacturer to manufacturer. Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		
Penetration time of glove material Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		
Butyl rubber gloves with a thickness of 0.4 mm are resistant to: Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		
Acetone: 480 min Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		
Butyl acetate: 60 min Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		
Ethyl acetate: 170 min Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.		
Xylene: 42 min Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance lengt of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.	~	
Butyl rubber gloves with a thickness of 0.4 mm are solvent resistant for 42-480 minutes. As protective measure, we recommend that users and responsible persons for work safety assume solvent resistance length of 42 minutes. Considering the data in section 3 of this SDS, one can assume longer resistance length in particular cases.	•	
	Butyl r	ubber gloves with a thickness of 0.4 mm are solvent resistant for 42- 480 minutes. As protective re, we recommend that users and responsible persons for work safety assume solvent resistance lengther.
	of 42 n	

Version number 4 (replaces version 3)

Safety data sheet according to Regulation (EC) No 1907/2006, Article 31

Revision: 27.03.2024

(Contd. of page 6)

GB

· Eye/face protection

Printing date 27.03.2024



Tightly sealed goggles

SECTION 9: Physical and chemical properties

SECTION 9: Physical and chemical prop	Jei lies
• 9.1 Information on basic physical and chemical p	properties
· General Information	•
· Physical state	Aerosol
· Colour:	According to product specification
· Odour:	Characteristic
· Odour threshold:	Not determined.
• Melting point/freezing point:	Undetermined.
· Boiling point or initial boiling point and boiling	onderermineu.
••••••••	Not applicable, as aerosol.
range Elammability	Not applicable.
· Flammability	Noi applicable.
· Lower and upper explosion limit	
· Lower:	1.5 Vol % (106-97-8 butane (containing < 0,1 %)
	butadiene (203-450-8)))
· Upper:	13 Vol % (67-64-1 acetone)
· Flash point:	Not applicable, as aerosol.
• Auto-ignition temperature:	365 °C (689 °F) (106-97-8 butane (containing < 0,1 %
	butadiene (203-450-8)))
· Decomposition temperature:	Not determined.
· pH	Mixture is non-soluble (in water).
· Viscosity:	· /
· Kinematic viscosity	Not determined.
· Dynamic:	Not determined.
· Solubility	
· water:	Not miscible or difficult to mix.
• Partition coefficient n-octanol/water (log value)	Not determined.
· Vapour pressure at 20 °C (68 °F):	8300 hPa (6225.5 mm Hg) (74-98-6 propane)
• Vapour pressure at 20 \circ C (06 \circ F). • Vapour pressure at 50 \circ C (122 \circ F):	
	16500 hPa (12376 mm Hg)
• Density and/or relative density	0.8 - () (6.7 lb - ())
• Density at 20 •C (68 •F):	$0.8 \ g/cm^3 \ (6.7 \ lbs/gal)$
· Relative density	Not determined.
· Vapour density	Not determined.
\cdot 9.2 Other information	
· Appearance:	
· Form:	Aerosol
· Important information on protection of health an	d
environment, and on safety.	
· Explosive properties:	Not determined.
· Solvent content:	
· Organic solvents:	90.2 %
· VOC (EC)	
	721.9 g/l
· VOC-EU%	90.24 %
	90.24 % 8.3 %
· Solids content:	0.3 70
· Change in condition	N / 1 11
· Evaporation rate	Not applicable.
· Information with regard to physical hazard classe	25
· Explosives	Void
	(C
	(Contd. on page 8

according to Regulation (EC) No 1907/2006, Article 31

Printing date 27.03.2024

Version number 4 (replaces version 3)

Revision: 27.03.2024

Trade name: HARDINOX - Stainless steel paint

	(Contd. of page
· Flammable gases	Void
·Aerosols	Extremely flammable aerosol. Pressurised container:
	May burst if heated.
• Oxidising gases	Void
· Gases under pressure	Void
· Flammable liquids	Void
· Flammable solids	Void
• Self-reactive substances and mixtures	Void
· Pyrophoric liquids	Void
· Pyrophoric solids	Void
· Self-heating substances and mixtures	Void
· Substances and mixtures, which emit flamm	able
gases in contact with water	Void
• Oxidising liquids	Void
· Oxidising solids	Void
· Organic peroxides	Void
· Corrosive to metals	Void
· Desensitised explosives	Void

SECTION 10: Stability and reactivity

· 10.1 Reactivity No further relevant information available.

· 10.2 Chemical stability

• Thermal decomposition / conditions to be avoided: No decomposition if used according to specifications.

- · 10.3 Possibility of hazardous reactions No dangerous reactions known.
- 10.4 Conditions to avoid No further relevant information available.
- 10.5 Incompatible materials: No further relevant information available.
- 10.6 Hazardous decomposition products: No dangerous decomposition products known.

SECTION 11: Toxicological information

· 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008

• Acute toxicity Based on available data, the classification criteria are not met.

67-64-1 ac	etone	
Oral	LD50	5800 mg/kg (rat)
Dermal	LD50	>15800 mg/kg (rabbit)
Inhalative	LC50 / 4h	76 mg/l (rat)
	LC50/96 h	5540 mg/l (oncorhynchus mykiss)
141-78-6 е	thyl acetate	
Oral	LD50	>18000 mg/kg (rab)
Dermal	LD50	5620 mg/kg (rat)
Inhalative	LC50/4 h	1600 mg/m3 (rat)
xylene		·
Oral	LD50	3523 mg/kg (rat)
Dermal	LD50	2000 mg/kg (rabbit)
Inhalative	LC50/4 h	29000 mg/m3 (rat)
Hydrocarb	oons, C9, aro	matics
Oral	LD50	>5000 mg/kg (rat) (OECD 401)
Dermal	LD50	>2000 mg/kg (rab) (OECD 402)

according to Regulation (EC) No 1907/2006, Article 31

Printing date 27.03.2024

Version number 4 (replaces version 3)

Revision: 27.03.2024

Trade name: HARDINOX - Stainless steel paint

		(Contd. of page 8)		
Hydrocar	bons, C10-C1	3, n-alkanes, isoalkanes,cyclics, < 2% aromatics		
Oral	LD50	>5000 mg/kg (rat) (OECD 401)		
Dermal	LD50	3160 mg/kg (rabbit) (OECD 402)		
· Skin corre	· Skin corrosion/irritation No irritant effect.			

· Serious eye damage/irritation Causes serious eye irritation.

· Respiratory or skin sensitisation No sensitising effects known.

· STOT-single exposure May cause drowsiness or dizziness.

· 11.2 Information on other hazards

· Endocrine disrupting properties

None of the ingredients is listed.

SECTION 12: Ecological information

•	12.1	Toxicity
---	------	----------

• Aquatic	toxicity:

67-64-1 acetone 8300 mg/l (fish) LC50/96h

EC50/96h

7200 mg/l (algae) LC50 / 48 h 8450 mg/l (crustacean (water flea))

xylene

EC50 / 48 h 7.4 mg/l (daphnia magna)

LC50/96 h 13.5 mg/l (fish)

Hydrocarbons, C9, aromatics

EC50/48 h 302 mg/l (daphnia magna)

EC50 / 72 h 2.75 mg/l (Pseudokirchneriella subcapitata)

EC50 / 96 h 9.2 mg/l (Regenbogenforelle)

· 12.2 Persistence and degradability No further relevant information available.

· 12.3 Bioaccumulative potential No further relevant information available.

· 12.4 Mobility in soil No further relevant information available.

· 12.5 Results of PBT and vPvB assessment

· **PBT:** Not applicable.

· vPvB: Not applicable.

· 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

· 12.7 Other adverse effects

· Remark: Harmful to fish

· Additional ecological information:

· General notes:

Water hazard class 2 (German Regulation) (Self-assessment): hazardous for water Do not allow product to reach ground water, water course or sewage system. Danger to drinking water if even small quantities leak into the ground. Harmful to aquatic organisms

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

· Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

(Contd. on page 10)

GB

Page 10/12

Safety data sheet

according to Regulation (EC) No 1907/2006, Article 31 Printing date 27.03.2024 *Version number 4 (replaces version 3)* Revision: 27.03.2024 Trade name: HARDINOX - Stainless steel paint (Contd. of page 9) · Uncleaned packaging: · Recommendation: Disposal must be made according to official regulations. Disposal must be made according to official regulations. **SECTION 14: Transport information** · 14.1 UN number or ID number UN1950 · ADR, IMDG, IATA · 14.2 UN proper shipping name 1950 AEROSOLS $\cdot ADR$ · IMDG AEROSOLS · IATA AEROSOLS, flammable · 14.3 Transport hazard class(es) · ADR 2 5F Gases. · Class · Label 2.1 · IMDG, IATA · Class 2.1 Gases. · Label 2.1 · 14.4 Packing group · ADR, IMDG, IATA not regulated · 14.5 Environmental hazards: Not applicable. · 14.6 Special precautions for user Warning: Gases. · Hazard identification number (Kemler code): · EMS Number: F-D, S-USW1 Protected from sources of heat. · Stowage Code SW22 For AEROSOLS with a maximum capacity of 1

· Segregation Code

SG69 For AEROSOLS with a maximum capacity of 1 litre: Segregation as for class 9. Stow "separated from" class 1 except for division 1.4. For AEROSOLS with a capacity above 1 litre: Segregation as for the appropriate subdivision of class 2. For WASTE AEROSOLS:

C, Clear of living quarters.

Segregation as for the appropriate subdivision of class 2.

litre: Category A. For AEROSOLS with a capacity above 1 litre: Category B. For WASTE AEROSOLS: Category

• 14.7 Maritime transport in bulk according to IMO instruments

Not applicable.

(Contd. on page 11)

GB

according to Regulation (EC) No 1907/2006, Article 31

Printing date 27.03.2024

Version number 4 (replaces version 3)

Revision: 27.03.2024

Trade name: HARDINOX - Stainless steel paint

1L	
Code: E0	
Not permitted as Excepted Quantity	
2	
D	
1L	
Code: E0	
Not permitted as Excepted Quantity	
UN 1950 AEROSOLS, 2.1	
	Code: E0 Not permitted as Excepted Quantity 2 D 1L Code: E0 Not permitted as Excepted Quantity

SECTION 15: Regulatory information

 \cdot 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

· Poisons Act

•	Regulated	explosives	precursors
---	-----------	------------	------------

None of the ingredients is listed.

· Regulated poisons

None of the ingredients is listed.

· Reportable explosives precursors

67-64-1 acetone

· Reportable poisons

None of the ingredients is listed.

· Directive 2012/18/EU

- Named dangerous substances ANNEX I None of the ingredients is listed.
- · Seveso category P3a FLAMMABLE AEROSOLS
- Qualifying quantity (tonnes) for the application of lower-tier requirements 150 t
- Qualifying quantity (tonnes) for the application of upper-tier requirements 500 t
- · 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

· Relevant phrases

- H220 Extremely flammable gas.
- H225 Highly flammable liquid and vapour.
- H226 Flammable liquid and vapour.
- H280 Contains gas under pressure; may explode if heated.
- H304 May be fatal if swallowed and enters airways.
- H312 Harmful in contact with skin.
- H315 Causes skin irritation.
- H317 May cause an allergic skin reaction.
- H319 Causes serious eye irritation.
- H332 Harmful if inhaled.
- H335 May cause respiratory irritation.
- H336 May cause drowsiness or dizziness.
- H351 Suspected of causing cancer.
- H372 Causes damage to organs through prolonged or repeated exposure.

(Contd. on page 12)

Listed

GB

Page 12/12

Printing date 27.03.2024

Safety data sheet

according to Regulation (EC) No 1907/2006, Article 31 Version number 4 (replaces version 3)

Revision: 27.03.2024

Trade name: HARDINOX - Stainless steel paint

(Contd. of page 11)
H373 May cause damage to organs through prolonged or repeated exposure.
H400 Very toxic to aquatic life.
H410 Very toxic to aquatic life with long lasting effects.
H411 Toxic to aquatic life with long lasting effects.
H412 Harmful to aquatic life with long lasting effects.
EUH066 Repeated exposure may cause skin dryness or cracking.
Classification according to Regulation (EC) No 1272/2008
Data is based on internal technical data and technical data from suppliers.
· Abbreviations and acronyms:
ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the
International Carriage of Dangerous Goods by Road)
IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association
GHS: Globally Harmonised System of Classification and Labelling of Chemicals
EINECS: European Inventory of Existing Commercial Chemical Substances
ELINCS: European List of Notified Chemical Substances
CAS: Chemical Abstracts Service (division of the American Chemical Society)
VOC: Volatile Organic Compounds (USA, EU)
DNEL: Derived No-Effect Level (UK REACH)
PNEC: Predicted No-Effect Concentration (UK REACH)
LC50: Lethal concentration, 50 percent
LD50: Lethal dose, 50 percent
PBT: Persistent, Bioaccumulative and Toxic
vPvB: very Persistent and very Bioaccumulative Flam. Gas 1A: Flammable gases – Category 1A
Aerosol 1: Aerosols – Category 1 Aerosol 1: Aerosols – Category 1
Press. Gas (Comp.): Gases under pressure – Compressed gas
Flam. Liq. 2: Flammable liquids – Category 2
Flam. Liq. 3: Flammable liquids – Category 3
Acute Tox. 4: Acute toxicity – Category 4
Skin Irrit. 2: Skin corrosion/irritation – Category 2
Eye Irrit. 2: Serious eye damage/eye irritation – Category 2
Skin Sens. 1: Skin sensitisation – Category 1
Carc. 2: Carcinogenicity – Category 2
STOT SE 3: Specific target organ toxicity (single exposure) – Category 3
STOT RE 1: Specific target organ toxicity (repeated exposure) – Category 1 STOT RE 2: Specific target organ toxicity (repeated exposure) – Category 2
Asp. Tox. 1: Aspiration hazard – Category 1
Aquatic Acute 1: Hazardous to the aquatic environment - acute aquatic hazard – Category 1
Aquatic Chronic 1: Hazardous to the aquatic environment - long-term aquatic hazard – Category 1
Aquatic Chronic 2: Hazardous to the aquatic environment - long-term aquatic hazard – Category 2
Aquatic Chronic 3: Hazardous to the aquatic environment - long-term aquatic hazard – Category 3
CLAIMER
STATISTICS ST

DISCLAIMER

The information contained in this sheet comes from reliable sources. It has been drawn up based on our knowledge at the time of the most recent update, as indicated. This information is intended as an aid to the user and should not be considered as a guarantee.

Conditions or methods of handling, storage, use or disposal of the product are outside our control, and we may not be held responsible for any loss, damage or expenses incurred as a result of, or in connection with, the latter.

All substances or mixtures can present unknown dangers and must be used with caution. We cannot guarantee that all dangers have been set out in an exhaustive manner.

This sheet has been drawn up for, and must be used for, this product only. If the product is used as a component in another product, the information given with it may not be applicable.

This sheet does not under any circumstances exempt the user from complying with all laws, regulations and administrative requirements related to the product, health and safety, and the protection of human health and the environment.